

### **SCALPIK L 20 NG**

ULTRA FAST IMMERSION LIQUID PAINT STRIPPER NEW GENERATION, WITHOUT METHYLENE CHLORIDE





#### **PACKAGING:**

- IBC HDPE container 1000l approved UN
- Blue 200l HDPE plastic drum approved UN
- Jerrican plastic HDPE 20I blue approved UN

# A REAS OF APPLICATION

SCALPIK L 20 NG is the fastest in its category. It is an optimised blend WITHOUT DICHLOROMETHANE, ideal for ferrous and non-ferrous METALS as well as WOOD.

SCALPIK L 20 NG has a very good biting power. This innovative paint pickling solution removes paints such as epoxy polyester, acrylics, vinyl, paints from cataphoresis, some varnishes and all uncured paints on ferrous metals and aluminium.

## APPLICATION

<u>CONCENTRATION</u>: ready to use <u>TEMPERATURE</u>: room temperature

STANDARD SEQUENCE OF USE: quenched application

**RINSING**: with high pressure washer

TREATMENT OF METALS AFTER PICKLING: After rinsing the pickled parts with SCALPIK L 20 NG, it is necessary to treat them with SCALP NEUTRALISER BASIC to avoid any oxidation of the support.

#### **REGENERATION OF THE BATH:**

- Supplement with new product.
- Scrubbing the paint flakes by using a sieve.

#### STORAGE:

Minimum storage temperature: +10°C

Maximum storage temperature: + 35 °C

Store in tightly closed containers, protected from air and light. If the product is not used within 12 months from the date of manufacture but storage conditions have been met then additional time may be allocated. In this case, contact our sales department.

#### PHYSICOCHEMICAL PROPERTIES

- Solvent base
- Density to 20°C: 1,06+/-0,05 g/cm
- Clear liquid, transparent
- Non-freezina
- Ph pure: 2 +/-0,5
- Flash point: 2° C

## PPLICATION PRECAUTIONS

Warning! Very flammable product. Remove the bath from all heat and flame sources. Do not allow any contact with skin or mucous membranes. Wear gloves, masks and glasses suitable for solvents. Work in a ventilated room. Handle by avoiding splashing. Consult the safety data sheet available upon request

Important: The content of this documentation is the result of our product experience. It can not engage our responsibility for its use in each particular case. It is also essential to carry out preliminary tests. Consult the Material Safety Data Sheet (MSDS)







