



SCALP PRIMER 36

WATER BASED INSULATING PRIMER FOR VERNASOLV PU 31 AND VERNAEAU PU 16











- Product of very high insulation
- Micro-porous
- Fast drying.
- Colourless.
- Odourless
- VOC-free



PACKAGING:

20 kg : pallet of 24 X 20 kg5 kg : carton of 4 X 5 kg

A REAS OF APPLICATION

SCALP PRIMER 36 is designed to act as an intermediate coat between the surface and coats of paint or varnish. It can also be used to isolate graffiti on a surface before painting. In the case of the polyurethane varnishes VERNASOLV PU 31 and VERNAEAU PU 16, it avoids wet surface appearance.

APPLICATION

- 1. DILUTION: Ready to use.
- 2. Tools: Roller; could be sprayed with an airless spray gun.
- **3. METHOD** Apply SCALP PRIMER 36, preferably in 2 fine coats and avoid overuse. Allow to dry and renew the operation a second time.
- **4. APPLICATION TIME**: Can be recoated after 24 hours on average (according to outside temperature).
- <u>5. APPLICATION TEMPERATURE</u>: From 5 to 50°C. Efficacy is reduced at extreme temperatures.
- **6. CLEANING OF TOOLS**: Clean tools in water immediately after use.
- 7. APPLICATION RATE: 80 to 130 g/m² according to surface.*
- **8. STORAGE:** Store the product in a frost-free location where it is protected from the weather and away from direct sunlight.

* Coverage areas are provided for information only and can be used to assess a project. They are in no way contractual; only tests can define the actual amount of product required depending on the surface to be treated.

CARACTERISTICAS FISICOQUIMICAS

- Water based viscous liquid
- White liquid
- Density: 1.05 +/- 0.03 g/cm3 at 20°C
- pH:8
- Not frost resistant
- Flash point: N/A
- Total dry extract: 30% 105°C,

A PPLICATION PRECAUTIONS

1. PROTECTION OF SURFACES: Do not apply to surfaces not intended to be insulated. 2. PROTECTION OF PERSONNEL: Avoid contact with eyes and skin. In case of contact, wash with water. Wear PVC gloves and glasses. Do not breathe fumes.

Important: The contents of this documentation result from our experience of the product. We cannot be held responsible for its use in each individual case. It is essential to test areas to be treated beforehand. See the Safety Data Sheet (SDS).





